

TECHNICAL INFORMATION

TOPFLOW SCREED A

Topflow Screed A is a pump-applied, free-flowing floor screed suitable for most applications, including underfloor heating.

Designed to provide a smooth level surface in both commercial and domestic buildings prior to the application of floor finishes, Topflow Screed A can be used bonded, unbonded or floating.

It is particularly suitable for use with underfloor heating.

For advice on specifications and for proprietary systems contact your Tarmac representative.

- Suitable for all residential and commercial floors carrying pedestrian traffic within BS8204 classification
- Compatible with the majority of timber frame construction systems due to its density at 40mm thickness (80kg/m²)

TOPFLOW SCREEN A BENEFITS

- It is a more conductive medium than sand cement screed and is self-curing and self-compacting
- It can be laid thinner than competing systems without detriment to its performance, so any underfloor heating pipes are closer to the surface (nominal cover to pipes 30mm)
- It can be force dried through the underfloor heating commissioning process as early as seven days after installation
- It can be laid as a floating construction over most types of rigid insulation board or acoustic matting at a minimum thickness of 40mm
- Environmentally friendly - a very sustainable choice with a synthetic calcium sulphate (gypsum) binder making a screed with over 36% recycled content and the ability to recycle 100% at the end of the building's life
- It offers significant programme benefits, as areas of up to 2,000m² can be easily laid in one day

- Its very low shrinkage values mean you require less construction joints than cement based screeds
- It is protein free and will not harbour bacteria
- It can receive foot traffic 48 hours after placing and partitions can be erected seven days after placing
- It is installed by trained and competent contractors who have invested in the necessary equipment to install the product correctly
- It is non-combustible and avoids the need for reinforcement

TOPFLOW SCREED A VERSUS CONVENTIONAL SAND CEMENT

TOPFLOW SCREED A	CONVENTIONAL SAND CEMENT	
Productivity	<ul style="list-style-type: none"> • Easily up to 2,000m² per day 	<ul style="list-style-type: none"> • Only 100 to 150m² per day
How quickly can you walk on the floor?	<ul style="list-style-type: none"> • Within 24 to 48 hours • Self-curing 	<ul style="list-style-type: none"> • Should not be walked on for seven days • Requires covering and curing
Joints	<ul style="list-style-type: none"> • 30-40 linear metres • Following building construction joints 	<ul style="list-style-type: none"> • Can be laid in small bays of between 5-7 linear metres
Performance	<ul style="list-style-type: none"> • Very low shrinkage • Minimal cracking • Will not curl 	<ul style="list-style-type: none"> • Shrinks • Cracks • Curls
Surface Finish	<ul style="list-style-type: none"> • Easily achieves SR2 under BS8204 	<ul style="list-style-type: none"> • Dependant on contractor • Curls and cracks at joints
On Insulation	<ul style="list-style-type: none"> • No reinforcement required • 40mm minimum thickness in commercial buildings • 35mm minimum thickness in domestic buildings 	<ul style="list-style-type: none"> • D49 or fibre reinforcement • 65mm minimum thickness
Average Drying Times	<ul style="list-style-type: none"> • 40 days at 40mm • Dependant on site conditions • Can be force dried after seven days 	<ul style="list-style-type: none"> • Nine weeks at 65mm thickness • Dependant on site conditions • Must dry naturally • Should be cured for one week
Unbonded floor construction	<ul style="list-style-type: none"> • Polythene laid directly to substrate minimal preparation • No reinforcement • 30mm minimum thickness 	<ul style="list-style-type: none"> • D49 or fibre reinforcement • 50mm minimum thickness
Quality control	<ul style="list-style-type: none"> • Produced under BS EN 13454 	<ul style="list-style-type: none"> • Often mixed on-site by hand with poor quality control • Inconsistent quality
Installation	<ul style="list-style-type: none"> • Self-compacting 	<ul style="list-style-type: none"> • Requires thorough compaction, one of the main reasons of failure
Environmentally friendly	<ul style="list-style-type: none"> • Contains over 36% recycled material 	<ul style="list-style-type: none"> • Cement manufacture uses 1.5 tonnes of CO²/tonne of cement produced
Health and Safety	<ul style="list-style-type: none"> • Ergonomically friendly installation • No cement burns 	<ul style="list-style-type: none"> • Very labour intensive
Underfloor heating	<ul style="list-style-type: none"> • High thermal conductivity • Reduced cover to heating elements 	<ul style="list-style-type: none"> • Low thermal conductivity
Cost	<ul style="list-style-type: none"> • In most applications Topflow Screed A gives cost/time savings over traditional hand applied sand and cement screed 	

TECHNICAL DATA

Appearance/Colour:	Off-white fluid mortar
Water Demand:	13-18 % b.w
pH:	>10
Wet Density:	2,200 kg/m ³
Dry Density:	2,000 kg/m ³

SPECIFICATION

Flow range	= 230mm-280mm
Maintenance of fluidity	= 2 hours
Compressive strength at 28 days	= CA25F4
Flexural strength at 28 days	= 4N/mm ²
Density	= 2,200kg/m ³
Thermal expansion	= 0.012mm/moK
Drying shrinkage at 28 days	= 0.02%
Thermal conductivity	= 2.0w/mK +/- 0.2
Fire rating (BS 476: Part 4)	= non-combustible

PRODUCT RANGE

Screed A	CA25 F4
Screed A Low Laitence	CA25 F4
Screed A XTR	CA35 F6
Screed A SoundBar	CA35 F6
Screed A Steeldeck	CA25 F4
Screed A Sky	CA25 F4/CA35 F6

MINIMUM THICKNESS

Bonded:	Minimum = 25mm
Unbonded over a solid base:	Nominal = 35mm Minimum = 30mm
Floating over thermal/sound insulation:	Minimum = 40mm
Cover over conduits/heating pipes:	Nominal = 30mm Maximum = 80mm

CONSIDERATIONS IN USE

- Topflow Screed A is not suitable as a wearing surface itself, or for external or permanently wet areas such as swimming pool surrounds
- The building should be weatherproof before screeding commences. Where applicable, especially on ground floors, there must be a damp-proof membrane below the screed or base
- The screed should only be laid when the internal air temperature is between 5°C and 30°C
- Cannot be laid to falls

FOLLOWING PLACING

No curing is required, however the floor should not be subjected to severe draughts, direct sunlight or heating for the first 48-72 hours to prevent rapid drying during this important early stage

The room in which the screed has been laid should therefore be sealed for a minimum of 48 hours. After this time the room should be ventilated. Windows and doors should then be closed at night and reopened during the day to allow further ventilation

DRYING

- The ambient conditions must be suitable for the drying of the screed with low air humidity (preferably 60% RH or less) and good ventilation
- Please note that moisture in the sub-base will impede the drying of the screed
- Before floor finishes are laid, the moisture content of the screed should be ascertained to be at, or below the required level
- Forced drying of Topflow Screed A is possible if required. After seven days heaters and dehumidifiers may be used to improve drying conditions
- The British standard for testing a base to receive a resilient floor covering is to use a Hair Hygrometer. This non-destructive test, when used strictly to the method defined in BS8203:2001, will give reliable results on Topflow Screed A floor screeds
- Drying time at 20°C 60% RH:
 - Up to 40mm thickness = 1 day/mm
 - Over 40mm thickness = 0.5 day/mm
- Topflow Screed A will require heavy sanding to remove laitance. This is recommended at 7-10 days to assist drying.
- Topflow Screed A low laitance will require light abrading to establish a mechanical key for subsequent floor coverings

FLOOR FINISHES

- Any type of floor finish can be applied to Topflow Screed A
- In order to ensure adhesion of floor coverings a primer that is compatible with floor covering adhesive must be used
- Before floor finishes are laid, the moisture content of the screed should be checked by the floor finish contractor

BREEAM

Concrete and screeds can play an extensive role within BREEAM and can directly and indirectly contribute to achieving a number of credits. Credits influenced are not limited to those regarding physical properties, but also those surrounding the delivery of the project and the practical use of the building.

BES 6001 RESPONSIBLE SOURCING

Tarmac Readymix is proud to have achieved a 'Very Good' rating under BES 6001 Responsible Sourcing Certification for all production sites and products. This 'Very Good' rating extends to our industry-leading brands such as Topflow Self-compacting Concrete and Topflow Screed A. This independent third-party certification scheme assesses responsible sourcing policies and practices throughout the supply chain; measuring the social, economic and environmental impacts of our concrete products over their whole life, from raw state, through manufacture and processing, through use, reuse and recycling, until its final disposal as waste. Topflow Screed A is supplied via Tarmac's network of screed manufacturing plants.

ENVIRONMENTAL

Topflow Screed A is produced using Gyvlon binder which is manufactured from an industrial by-product. Topflow Screed A - Average 36% recycled content. Recyclability - 100% recyclable. Volatile Organic Compound (VOC) free.

PRECAUTIONS OF USE

SAFETY

The use of safety goggles, hard hat, ear defenders and gloves is recommended when placing concrete and screed.

FIRST AID

EYES

Immediately flush eyes, including under lids, with water for at least 15 minutes to remove all particles. If necessary, seek medical advice.

SKIN

Wash skin with cold water and a pH neutral soap as soon as possible, except where open wounds are visible. Attention should be paid to wounds and fresh scars which should be covered with protective paraffin gauze. Seek medical help in cases of prolonged contact with wet concrete.

INGESTION

Rinse mouth with clean water. If swallowing has occurred drink plenty of milk or water. Do not induce vomiting. Seek medical attention immediately.

INHALATION

Move to fresh air. If symptoms persist seek medical attention.

For more details contact

0800 1218 218

enquiries@tarmac.com

topflow@tarmac.com

The information given in this technical data sheet is based on our current knowledge and is intended to provide general notes on our products and their uses. Tarmac endeavour to ensure that the information given is accurate, but accept no liability for its use or its suitability for particular application because of the product being used by the third party without our supervision. Any existing intellectual property right must be observed.