

Tarmac Cement
National Laboratory
Yelsway Lane
Waterhouses
Staffordshire
ST10 3AZ

15/11/2024

Composition of Fly ash

**Tudela Fly Ash
EN 450-1 LOI Cat. B, Fineness Cat.N
0086-CPR-756089**

Based on the **September 2024** monthly composite sample: 3470

Property			Value	BS EN 450-1 Limit
Fineness (Residue)	45µm	%	10.3	Declared Value 15% ± 10% <i>(Tested in accordance with BS EN 450-1 cl. 5.3.1)</i>
APD		g/cm ³	2.51	< 200kg/m ³ from declared value
28 Day Activity Index – Aug sample		%	78	>75%
90 Day Activity Index – July sample		%	85	>85%
Sulfate	SO ₃	%	1.33	≤ 3.0%
Loss on Ignition	LOI	%	3.76	≤ 7.0%
Chloride	Cl ⁻	%	0.01	≤ 0.1%
Calcium Oxide	CaO	%	6.84	≤ 10.0%
SiO ₂ + Al ₂ O ₃ + Fe ₂ O ₃	-	%	81.20	≥ 70.0%
Free Lime	-	%	0.35	≤ 1.5%
Alkalis	Na ₂ Oeq	%	1.17	≤ 5.0%
Declared Mean Alkali Content	Na ₂ Oeq	%	1.50	-
Declared Maximum Chloride Content	Cl ⁻	%	0.05	-

*BS EN 933-10:2009 method replacing the 63 µm sieve with a 45 µm sieve

For and on behalf of Tarmac Cement:



Simon Chudley

**National Commercial Technical Manager
Tarmac Cement**

TARMAC.COM

Tarmac Trading Limited Registered in England and Wales. Company No. 453791
Tarmac Cement Limited Registered in England and Wales. Company No. 66558
Tarmac Services Limited Registered in England and Wales. Company No. 8197397
Registered address for all companies: T3 Trinity Park, Bickenhill Lane, Birmingham, B37 7ES

T3 Trinity Park, Bickenhill Lane,
Birmingham, B37 7ES
0345 812 6232 info-cement@tarmac.com

**Conformity of Fly Ash to BS 8500-2: Annex B
Tudela EN 450-1 Fly Ash
0086-CPR-756089**

Based on the composite samples for the month of: September 2024

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Aberthaw

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	20.3
28 Day Strength (MPa)	46.6

Based on equivalent results obtained for the last 12 months, the permitted proportions of combinations conforming to the requirements of Annex B of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	18	35
42,5N	6	26

BS 8500-2 Combination Designation	Fly Ash Content (%)	
	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley



National Commercial Technical Manager Tarmac Cement
TARMAC.COM

**Conformity of Fly Ash to BS 8500-2: Annex B
Tudela EN 450-1 Fly Ash
0086-CPR-756089**

Based on the composite samples for the month of: September 2024

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Cauldon

The results of compressive strength testing (in accordance with BS EN 196-1)
of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	12.1
28 Day Strength (MPa)	36.4

Based on equivalent results obtained for the last 12 months, the permitted proportions of combinations conforming to the requirements of Annex B of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	9	35
42,5N	6	20

BS 8500-2 Combination Designation	Fly Ash Content (%)	
	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley



National Commercial Technical Manager Tarmac Cement
TARMAC.COM

**Conformity of Fly Ash to BS 8500-2: Annex B
Tudela EN 450-1 Fly Ash
0086-CPR-756089**

Based on the composite samples for the month of: September 2024

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Dunbar

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	18.1
28 Day Strength (MPa)	45.6

Based on equivalent results obtained for the last 12 months, the permitted proportions of combinations conforming to the requirements of Annex B of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	18	35
42,5N	6	25

BS 8500-2 Combination Designation	Fly Ash Content (%)	
	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley



National Commercial Technical Manager Tarmac Cement
TARMAC.COM

**Conformity of Fly Ash to BS 8500-2: Annex B
Tudela EN 450-1 Fly Ash
0086-CPR-756089**

Based on the composite samples for the month of: September 2024

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Limerick

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	18.0
28 Day Strength (MPa)	44.5

Based on equivalent results obtained for the last 12 months, the permitted proportions of combinations conforming to the requirements of Annex B of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	16	35
42,5N	6	25

BS 8500-2 Combination Designation	Fly Ash Content (%)	
	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley



National Commercial Technical Manager Tarmac Cement
TARMAC.COM

**Conformity of Fly Ash to BS 8500-2: Annex B
Tudela EN 450-1 Fly Ash
0086-CPR-756089**

Based on the composite samples for the month of: September 2024

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Platin

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	18.8
28 Day Strength (MPa)	44.5

Based on equivalent results obtained for the last 12 months, the permitted proportions of combinations conforming to the requirements of Annex B of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	15	35
42,5N	6	24

BS 8500-2 Combination Designation	Fly Ash Content (%)	
	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley



National Commercial Technical Manager Tarmac Cement
TARMAC.COM

**Conformity of Fly Ash to BS 8500-2: Annex B
Tudela EN 450-1 Fly Ash
0086-CPR-756089**

Based on the composite samples for the month of: September 2024

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Rugby

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	18.3
28 Day Strength (MPa)	46.8

Based on equivalent results obtained for the last 12 months, the permitted proportions of combinations conforming to the requirements of Annex B of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	16	35
42,5N	6	26

BS 8500-2 Combination Designation	Fly Ash Content (%)	
	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley



National Commercial Technical Manager Tarmac Cement
TARMAC.COM

**Conformity of Fly Ash to BS 8500-2: Annex B
Tudela EN 450-1 Fly Ash
0086-CPR-756089**

Based on the composite samples for the month of: September 2024

Constituent	Source
EN 450-1 Fly Ash	Tudela
EN 197-1 CEM I	Tunstead

The results of compressive strength testing (in accordance with BS EN 196-1) of a 70:30 blend of CEM I with Fly Ash were:

2 Day Strength (MPa)	20.0
28 Day Strength (MPa)	51.9

Based on equivalent results obtained for the last 12 months, the permitted proportions of combinations conforming to the requirements of Annex B of BS 8500-2 are:

Strength Class of Combination	Fly Ash Content (%)	
	Min	Max
32,5N	21	35
42,5N	6	32

BS 8500-2 Combination Designation	Fly Ash Content (%)	
	Min	Max
CIIA-V	6	20
CIIB-V	21	35

For and on behalf of Tarmac Cement:

Simon Chudley



National Commercial Technical Manager Tarmac Cement
TARMAC.COM

Tarmac Cement Limited Registered in England and Wales. Company No. 66558
Registered address: T3 Trinity Park, Bickenhill Lane, Birmingham, B37 7ES